

LOCTITE[®] 549™

July 2012

PRODUCT DESCRIPTION

LOCTITE[®] 549[™] provides the following product characteristics:

Technology	Acrylic			
Chemical Type	Dimethacrylate ester			
Appearance (uncured)	Orange liquid ^{LMS}			
Components	One component - requires no mixing			
Viscosity	Medium, thixotropic			
Cure	Anaerobic			
Application	Gasketing and Sealing			
Strength	Medium			

LOCTITE[®] 549[™] is a ready-to-use, single component, gel-like anaerobic thread sealant that cures at room temperature when it is isolated from air contact. This product seals close fitting joints between rigid metal faces and flanges. It provides an instant seal to low pressures immediately after assembly of flanges. Typical application is as a formed-in-place gasket for pumps, thermostats, compressors, transmission housings and axle covers.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Weight per volume	kg/L	1.2
	(lbs/gal)	(10.1)
Flash Point - See MSDS		
Viscosity, Brookfield - RVT, 25 °C, mPa·s (cP):	
Spindle 6, speed 20 rpm,	10,000 to 35,0	000 ^{lms}

TYPICAL CURING PERFORMANCE

Cure Speed vs. Substrate

The rate of cure will depend on the substrate used. The graph below shows the shear strength developed with time on grit blasted steel lap shears compared to different materials and tested according to ISO 4587.



Cure Speed vs. Temperature

The rate of cure will depend on the ambient temperature. The graph below shows the shear strength developed with time on grit blasted steel lap shears at different temperatures and tested according to ISO 4587.



TYPICAL PERFORMANCE OF CURED MATERIAL Adhesive Properties

Cured for 24 hours @ 22 °C		
Compressive Shear Strength, ISO 10123:		
Steel pins and collars	N/mm² (psi)	≥15.2 ^{LMS} (≥2,200)
Tensile Strength, ISO 6922, N/mm ² (psi):		
Steel pin to Steel pin	N/mm² (psi)	7.7 (1,120)

Cured for 72 hours @ 22 °C		
Lap Shear Strength, ISO 4587:		
Steel (grit blasted)	N/mm²	3.6
	Inell	15200

TYPICAL ENVIRONMENTAL RESISTANCE

The following tests refer to the effect of environment on strength. This is not a measure of sealing performance.

Cured for 1 week @ 22 °C Lap Shear Strength, ISO 4587: Steel (grit blasted)



Hot Strength



Heat Aging





Chemical/Solvent Resistance

Aged under conditions indicated and tested @ 22 °C

		% of initial strength			
Environment	°C	250 h	500 h	750 h	1000 h
Motor oil	125	190	220	235	220
Water/glycol 50/50	87	160	165	115	105
Gasoline	22	75	40	55	40

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Where aqueous washing systems are used to clean the surfaces before bonding, it is important to check for compatibility of the washing solution with the adhesive. In some cases these aqueous washes can affect the cure and performance of the adhesive.

This product is not normally recommended for use on plastics (particularly thermoplastic materials where stress cracking of the plastic could result). Users are recommended to confirm compatibility of the product with such substrates.

Directions for use:

- 1. For best performance bond surfaces should be clean and free from grease.
- 2. The product is designed for close fitting flanged parts with gaps up to 0.25mm (0.010 inches).
- 3. Apply manually as a continuous bead or by screen printing to one surface of the flanges.
- Low pressures (<0.5 bar, <5 psi) may be used when testing to confirm a complete seal immediately after assembly and before curing.
- 5. Flanges should be tightened as soon as possible after assembly to avoid shimming.

Loctite Material Specification^{LMS}

LMS dated February 28, 2012. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 °C to 21 °C. **Storage below** 8 °C or **greater than 28** °C **can adversely affect product properties**. Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

 $(^{\circ}C \ge 1.8) + 32 = ^{\circ}F$ kV/mm x 25.4 = V/mil mm / 25.4 = inches μ m / 25.4 = mil N x 0.225 = lb N/mm x 5.71 = lb/in N/mm² x 145 = psi MPa x 145 = psi N·m x 8.851 = lb·in N·m x 0.738 = lb·ft N·mm x 0.142 = oz·in mPa·s = cP

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. [®] denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.0